Technical Data Sheet



	Rev.1 10/2017
FEATURES	
	MD Grey Primer as anti-corrosive pigment and a special alkyd as vehicle agent.
	MD Grey Primer is a general purpose, economical primer for metal before topcoat with
	MD Enamel Gloss. It is characterized with drying, good flow and good adhesion for metal substrate.
	It is primer for iron, steel of general construction, such as fabricated steel, machineries,
	iron rails, gates, grills for the windows, ect.
TECHNICAL INFORMATION	
Туре	Anti-corrosive Primer
Color	Grey
Film appearance	Matt
Solid by volume	68%
Solid by weight	80%
Flash point	40 °C
Volatile organic compounds (VOCs)	- gram / liter
Wet film thickness	77 microns
Dry film thickness	40 microns
Theoretical coverage.	12 sqm. / liter / coat
	45 sqm. / gallon / coat
	Remark - Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition
	method and technique; as well as the structure and dimensions of the object to be coated.
Touch dry (25-30°C)	20 -40 minutes.
Recoat dry (25-30°C)	5-6 hours.
Full cure (25-30°C)	5-6 days.
REFERENCE STANDARD	
	-
4 P.D. 10 4 T.O.1	
APPLICATION	
Tools	Roller, Brush, Spray
Thinner No.	TOA Thinner No.23 , TOA Thinner No.21
Dilution (%)	10 -15 %
APPLICATION SYSTEM	
Surface Preparation	
New surface (Steel)	Steel substrate must be prepared ,free from rust,millscale,dirt,loose particles,and waxy contaminate.
	Wood substrate must be prepared ,free from dirt,loose particles,and waxy contaminate.
Old surface (Steel)	Polishing the paint film peeling out and clean the dust, rust and grease-free
Coating system	
Primer Steel	: MD Grey Primer 1-2 coat . (40 μ per coat)
Primer Alloy	: TOA Wash Primer for galvanized steel and aluminium alloy surface (10 μ per coat)
	: MD Grey Primer 1-2 coat . (40 μ per coat)
Topcoat	: MD Enamel gloss 2 coat (25 μ per coat)

Technical Data Sheet



D drey i fillier	
Recommendation	Rev.1 10/2017 : The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of
	the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is required in confined areas to ensure correct drying.
HANDLING AND STORAGE	
Storage condition	: The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.
Shelf life	: 12 months at 30 °C
HEALTH AND SAFETY	
	 : Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately. : For detailed information on the health and safety hazards and precautions for use of this product,
	we refer to the Material Safety Data Sheet.
DISCLAIMER	: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.